



## AGGLO STILL

Parameter	Tolerance
Height (mm)	nominal $\pm$ 0,5
Diameter (mm)	nominal $\pm$ 0,4
Ovalization (mm)	0-0,3
<b>Moisture</b>	4% - 8%
<b>Peroxide content</b>	(mg O <sub>2</sub> /cork) < 0,1
<b>Dust content</b>	(mg/cork) < 1,5
<b>Extraction force</b>	daN 20-35

### Warnings

Keep the corks in original packaging and in a clean and ventilated room. Avoid contacts with any product containing chemicals and fuels. The ideal storage temperature is between 15°C and 20°C, with a relative humidity between 50% and 70%. Open the bags only at the moment of use and reseal unused corks. We recommend the use within 6 months from delivery.

Intersugheri has the right to change product specifications at any time and without notice, in total respect of the laws in force and in accordance with the manual "Disciplinare del Sughero" (The new discipline on analytical methods for the control of oenological cork).